

HAERING



WIR BEKENNEN FARBE



Haering	SATAjet 1000 B RP	SATA spray master RP	SATAjet 4800 K spray mix	SATAjet 3000 K spray mix
HAERAPUR Aqua 2K-Decklack BW59 1 K	1.6	--	--	--
	2.5 bar	--	--	--
HAERATEX Aqua 2K-Rauheffektlack BW87 21 K	1.6 / 1.8 / 2.0	--	--	--
	1.0 - 2.0 bar	--	--	--
HAERAFLEX 1K-Spezialhaftprimer H001031	1.3 / 1.6 / 1.8	--	--	2850 / 3350
	1.0 - 2.0 bar	--	--	2.0 - 3.0 bar
HAERACRYL Aqua 1K-Kunststoffgrund HW2-K	1.3 / 1.6	SM	3350 / 3850	3350 / 3850
	2.0 bar	2.0 - 3.0 bar	2.5 - 3.0 bar	2.5 - 3.0 bar
HAERACRYL Aqua 1K-Es- Kunststofflack HW4-K	1.3 / 1.6	SM	3350 / 3850	3350 / 3850
	1.0 - 1.5 bar	1.5 - 2.5 bar	3.0 bar	3.0 bar
HAERACRYL Aqua 1K-Strukturlack HW89 1 K	2.0	--	--	--
	1.5 - 2.5 bar	--	--	--
HAERAPOX HS 2K-Grundierung A2?.72	2.0 / 2.5 HV	--	--	--
	1.5 - 2.5 bar	--	--	--
HAERAPOX 2K-Grundierung/grau A27 15	1.6 / 1.8 / 2.0	--	--	--
	1.5 - 2.0 bar	--	--	--
HAERAPOX HS 2K-Einschichtlack A4?.77	1.3 / 1.6	--	--	--
	1.5 - 2.0 bar	--	--	--
HAERATHANE 2K-Grundierung B27 6	2.0 / 2.5 HV	--	--	--
	1.0 - 1.5 bar	--	--	--
HAERATHANE 2K-Einschichtlack B5?.32	1.3 / 1.6	--	2850 / 3350	2850 / 3350
	1.0 - 2.0 bar	--	2.0 - 3.0 bar	2.0 - 3.0 bar


¹⁾Luftdüsendruck | air cap pressure | Pression à l'intérieur du chapeau d'air

*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.

HAERING



WIR BEKENNEN FARBE



Haering	SATAjet 1000 B RP	SATA spray master RP	SATAjet 4800 K spray mix	SATAjet 3000 K spray mix
HAERAPUR 2K-Decklack B7 glänzend	1.3 / 1.6	--	2850 / 3350	2850 / 3350
	1.0 - 2.0 bar	--	2.0 - 3.0 bar	2.0 - 3.0 bar
HAERAPUR 2K-Strukturlack B8?.17	2.0 / 2.5 HV	--	--	--
	1.5 - 2.0 bar	--	--	--
HAERADUR 2K-ES-Strukturlack B8?.24	2.0 / 2.5 HV	--	--	--
	1.5 - 2.0 bar	--	--	--
HAERAPUR 2K-Strukturlack B8?.46	2.0 / 2.5 HV / 3.0 HV	--	--	--
	1.5 - 2.0 bar	--	--	--
HAERALKYD HS-Grund K2?.72	1.6 / 1.8	--	2850 / 3350	2850 / 3350
	1.0 - 1.5 bar	--	2.5 - 3.0 bar	2.5 - 3.0 bar
HAERALKYD 1K HS-Einschichtlack K4?.72	1.3 / 1.6	--	2850 / 3350	2850 / 3350
	2.0 bar	--	2.5 - 3.0 bar	2.5 - 3.0 bar

¹⁾Luftdüsendruck | air cap pressure | Pression à l'intérieur du chapeau d'air

*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. |
 Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.